

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 09-259419

(43)Date of publication of application : 03.10.1997

(51)Int.Cl.

G11B 5/66

G11B 5/85

H01F 10/16

(21)Application number : 08-090019

(71)Applicant : HITACHI MAXELL LTD

(22)Date of filing : 19.03.1996

(72)Inventor : ADACHI KAZUNORI

MARO TAKESHI

ISHIZAKI OSAMU

ONUKE TAKESHI


SAKAMOTO AKITO

(54) MAGNETIC RECORDING MEDIUM AND ITS PRODUCTION

(57)Abstract:

PROBLEM TO BE SOLVED: To produce a magnetic recording medium having high coercive force and generating low noise.

SOLUTION: An underlayer, a CoCrPt magnetic layer and a protective layer are successively formed on a nonmagnetic substrate to obtain the objective magnetic recording medium. The magnetic layer contains 5.0-16.5at.% oxygen in a dispersed state. At the time of forming the magnetic layer by sputtering, a gaseous oxygen-argon mixture is used as sputtering gas and 5.0-16.5at.% oxygen is incorporated into the magnetic layer by regulating the mixing ratio of oxygen. The C-N ratio of the resultant magnetic recording medium is remarkably increased. A resin



BEST AVAILABLE COPY

substrate may be used as the nonmagnetic substrate.

LEGAL STATUS

[Date of request for examination] 25.06.2002

[Date of sending the examiner's decision of rejection] 25.03.2003

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision 2003-06853 of rejection]

[Date of requesting appeal against examiner's decision of rejection] 23.04.2003

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

BEST AVAILABLE COPY